

Temperature Equivalents Orton Cones (°C)

cone-no.	heating rate (°C / hour)		cone-no.	heating rate (°C / hour)	
	60	150		60	150
LRB 019	676	693	SSB 10	1285	1305
LRB 018	712	732	LRB 11	1293	1312
LRB 017	736	761	LRB 12	1304	1326
LRB 016	769	794	SSB 12	1306	1326
LRB 015	788	816	LRB 13	1321	1346
LRB 014	807	836	SSB 13	1331	1348
LRB 013	837	859	SSB 13 1/2	1352	1367
LRB 012	858	880	SSB 14	1365	1384
LRB 011	873	892	LRB 14	1388	1366
IFB 010	884	891	LRB 15	1424	1431
IFB 09	917	926	LRB 16	1455	1473
IFB 08	945	955	LRB 17	1477	1485
IFB 07	970	980	LRB 18	1500	1506
IFB 06	991	996	LRB 19	1520	1528
IFB 05 1/2	1011	1020	LRB 20	1542	1549
IFB 05	1032	1044	LRB 21	1564	1569
IFB 04	1060	1067	LRB 23	1586	1590
IFB 03	1087	1091	LRB 26	1589	1605
IFB 02	1102	1113	LRB 27	1614	1627
IFB 01	1122	1132	LRB 28	1619	1633
IFB 1	1137	1146	LRB 29	1624	1645
LRB 2	1142	1162	LRB 30	1636	1654
IFB 3	1151	1160	LRB 31	1661	1679
LRB 4	1160	1181	LRB 31 1/2	1684	1698
LRB 5	1184	1205	LRB 32	1706	1717
LRB 6	1220	1241	LRB 32 1/2	1718	1730
LRB 7	1237	1255	LRB 33	1732	1741
LRB 8	1247	1269	LRB 34	1757	1759
LRB 9	1257	1278	LRB 35	1784	1784
LRB 10	1282	1303	LRB 36	1798	1796

BTN : 6903.20.90 | Packing LRB/IFB: 50 pcs / box | Packing SSB: 25 pcs / box